



GRADE RING EXTENSIONS			
WEIGHTS, LBS.			
I.D.	O.D.	AVAILABLE HEIGHTS	LBS./IN.
24"φ	40"φ	2", 4", 6", 12", 18", 24"	70
30"φ	46"φ	2", 4" & 6"	85

GENERAL NOTES:

- 1) CONCRETE TO TEST 4,000 PSI AT 28 DAYS.
- 2) DESIGNED TO WITHSTAND AASHTO H-20 LOADING
- 3) REINFORCING STEEL PER ASTM A185 FOR WELDED WIRE FABRIC (W.W.F.) AND ASTM A615, GRADE 60 - BLACK BARS
- 4) AIR ENTRAINED: 5.0% - 9.0%



7 Ruscitti Road
 New Windsor, New York, 12553
 www.arconcrete.com
 845-562-0640

STOCK
 PRECAST CONCRETE GRADE RINGS

DATE: 7/8/2019

REV.: 8/16/2019

DWN.BY: A&R LLC

DWG. NO.:
 GRADERINGS