


GRADE RING EXTENSIONS			
I.D.	O.D.	AVAILABLE HEIGHTS	LBS/IN
24"	40"	2", 4", 6", 12", 18", 24"	70
30"	46"	2", 4", 6"	85

NOTES:

- 1) CONCRETE TO TEST 4,000 PSI AT 28 DAYS.
- 2) DESIGNED TO WITHSTAND AASHTO H-20 LOADING.
- 3) REINFORCING STEEL PER ASTM A185 FOR WELDED WIRE FABRIC (W.W.F.) AND ASTM A615, GRADE 60 - BLACK BARS.
- 4) AIR ENTRAINED: 5.0% - 9.0%.

WEIGHT

POUNDS

	276 Clove Road Salisbury Mills, New York, 12577 www.arconcrete.com 845-562-0640	
		DATE: 8/31/2022
GRADE RINGS		REV.: ---
CONTRACTOR: ---		DWN.BY: A&R LLC
		DWG. NO.: GR